



KGF



Bare annealed copper

STANDARDS APPLIED

**Construction : IEC 60228
CENELEC HD 383**

Specific resistance		Maximum 17.241 ohm*mm ² /km
Tensile strength		Approx. 240 N/mm ²
Elongation at break		Approx. 20 - 30%

KGF

Annealed, stranded copper wire. IEC 60228 Class 2

DIMENSIONS

Cross section mm²	No. of wires and wire-diameter	Art. No.	Outer diameter appr. mm	Appr. weight Kg per 100m
10	7x1,35	130930	4,1	8,9
16	7x1,71	130935	5,2	13,9
25	7x2,12	130940	6,4	22,0
35	7x2,50	130950	7,6	30,8
50	7x2,88	130958	9,0	41,2
70	19x2,12	130960	11,0	60,4
95	19x2,50	130970	12,6	85,0
120	37x2,01	130975	14,2	107,0
150	37x2,28	130977	15,9	131,2